

LANXESS BROMOBUTYL 2030

Product Description

A non-staining, brominated isobutylene-isoprene copolymer with low Mooney viscosity

Supply Form

Off-white bales

Raw Material Properties

Property	Nominal Value	Unit	Test Method
Mooney Viscosity ML (1+8) 125°C	32 ± 4	MU	ISO 289 / ASTM D 1646
Volatile Matter	max. 0.7	wt %	ISO 248 / ASTM D 5668
Total Ash	max. 0.7	wt %	ISO 247 / ASTM D 5667
Bromine Content	1.8 ± 0.20	wt %	(*)
Antioxidant non-staining	min. 0.03	wt %	(*)
Stabilizer	1.3 ± 0.3	wt %	(*)

(*) LANXESS standard test method available on request

Other Product Features

Property	Typical Value		
Density	0.93	g/cm³	
Cure Characteristics	Rotorless cure meter conditions: 160°C, 1° arc, 1.7 Hz die oscillation, 30 min running time, no preheat		
	M _L	4.3 ± 0.8 dNm	ISO 6502 / ASTM D 5289
	M _H	12.5 ± 2.2 dNm	ISO 6502 / ASTM D 5289
	ts1	2.7 min.	ISO 6502 / ASTM D 5289
	tc90	9.0 ± 2.2 min.	ISO 6502 / ASTM D 5289
Test Formulation	MIM mixed compound: according to ISO 7663 / ASTM D 3958		
	LANXESS	100 (parts by mass)	
	BROMOBUTYL 2030		
	IRB #7 black	40	
	NBR Stearic acid	1	
	NBS Zinc oxide	5	

LANXESS BROMOBUTYL 2030

Packaging	34 kg bales in dispersible EVA film (Vicat softening point max. 80°C, ISO 306 / ASTM D 1525) or strippable PE film (Melting point max. 105°C, ASTM D 3418); pallets of 30 bales (1020 kg)
Storage Life/Conditions	2 years from date of production at temperatures not exceeding 35°C and protected against sunlight.
Product Safety	Relevant safety data and references as well as the possibly necessary warning labels can be found in safety data sheet no. 440713.

These raw material properties are typical and, unless specifically indicated otherwise, are not to be considered as delivery specification.

Issue number: Nr.1 / Date of issue: March 26, 2007 / Previous issue from March 15, 2005

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.